



# Exelene<sup>®</sup> LLDPE

## Product Data Sheet

### Linear Low-Density Polyethylene

### LLDPE-butene

### Injection Molding

# 20400

Melt Flow Rate **20,0**

Density **0,925**

#### Applications

- Trash cans and office paper bins, Christmas Trees
- Ice trays, Ice Cream cup lids and Twist off bottle caps with security seals.
- Compound Extrusion (Additive and Color Concentrates)

#### Characteristics

- The Exelene resin LLDPE 20400 meets the requirements of section 177.1520, paragraph C, from chapter 21 denominated "Olefin Polymers" from the Code of Federal Regulations of the FDA, to be utilized with direct food contact.

Properties		ASTM Testing	Units	Values
<b>Resin Properties</b>				
Melt Flow Rate	MFI <sub>2</sub>	D 1238 (190°C; 2,16 kgf)	g/10 min	20.00
Density		D 792 (23°C)	g/cm <sup>3</sup>	0.925
Melting Point		DSC	°C	124
Additives Package		Antioxidant		
<b>Properties in standard test tubes by injection molding</b>				
Tensile Strength @ yield		D 638 (50 mm/min, IV)	psi	1,595
Elongation @ break		D 638 (50 mm/min, IV)	%	350
Flexural Modulus (1%)		D 790 I/B (13 mm/min; 3,2 mm)	psi	37,350
Tensile Impact Strength		D 1822 (S, 23°C)	ft x lb / in <sup>2</sup>	80
Durometer Hardness (Shore D)		D 2240 D (23°C; 1 s)	----	50
Brittleness Temperature		D 746A (F50; 25 lbfXin)	°C	< -76
Vicat Softening Point		D 1525A (50°C/h; 1,0 kgf)	°C	94.8
Deflection Temperature Under Load		D 648 (2°C/min; 66 psi)	°C	43
ESCR	Condition B <sup>(1)</sup>	D 1693B (F50; 1,9 mm)	h	20

(1) Condition B : Grooved specimen with thickness of 1,905 mm = 0,075 in in 100 % Igepal CO-630 a 50°C

